

Mallard Creek Polymers BarrierPro® 4550 SBR Emulsion

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE), Styrene Butadiene Rubber

Material Notes:

BARRIER PRO® 4550 is an anionic carboxylated styrene-butadiene copolymer latex containing a non-staining antioxidant. Features: highly stable, good compatibility with fillers and pigments, etc., cured films are tough and flexible, cured films have good water resistance, hydrolysis resistant. STORAGE AND HANDLING: Protect from freezing. Ideal storage temperature is 22°C (72°F). Stability at 22°C (72°F) is 180 days when properly stored. Read the BARRIER PRO® 4550 Material Safety Data Sheet before handling, storing, or using this product.APPLICATIONS: BARRIER PRO® 4550 is a general purpose latex binder of medium stiffness. It dries to form a flexible, tough film of high water resistance. BARRIER PRO® 4550 can be compounded with fillers and other additives to form coatings for a variety of applications such as damp proof membranes, specialty paints and sealants.Information provided by Mallard Creek Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-BarrierPro-4550-SBR-Emulsion.php

Physical Properties	Metric	English	Comments
Solids Content	49 - 51 %	49 - 51 %	
рН	9.5 - 10	9.5 - 10	
Brookfield Viscosity	<= 900 cP	<= 900 cP	#2/20 rpm

Thermal Properties	Metric	English	Comments	
Glass Transition Temp, Tg	1.00 °C	33.8 °F		

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China