

## Mallard Creek Polymers ROVENEÂ® 6017 Styrene-Acrylic Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Styrene Butadiene Rubber

### Material Notes:

ROVENEÂ® 6017 is a stiff, self-crosslinking styrene-acrylic copolymer emulsion with excellent water resistance and good mechanical stability. APPLICATIONS: ROVENEÂ® 6017 is recommended for bonding nonwovens such as highloft webs, medical applications, and interlinings. Information provided by Mallard Creek Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Mallard-Creek-Polymers-ROVENE-6017-Styrene-Acrylic-Emulsion.php](http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-ROVENE-6017-Styrene-Acrylic-Emulsion.php)

Physical Properties	Metric	English	Comments
Solids Content	44 - 46 %	44 - 46 %	
Particle Size	0.20 Âµm	0.20 Âµm	
pH	4.0 - 5.0	4.0 - 5.0	
Brookfield Viscosity	<= 100 cP	<= 100 cP	#2/20 rpm

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	35.0 Â°C	95.0 Â°F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	
Residual Monomer	0.02% Max	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China