

Mallard Creek Polymers Rovene® 6025 Styrene-Acrylic Emulsion

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Applications: Rovene® 6025 can be used in multiple coating and paint applications including landscaping coatings and low sheen interior flat wall coatings. It can also be used as a binder for dust suppression and soil stabilization. Rovene® 6025 can be spray applied and coated by traditional methods.**Storage and Handling:** Protect from freezing. Ideal storage temperature is 22°C (72°F). Read the Rovene® 6025 Material Safety Data Sheet before handling, storing, or using this product. Information provided by Mallard Creek Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mallard-Creek-Polymers-Rovene-6025-Styrene-Acrylic-Emulsion.php

Physical Properties	Metric	English	Comments
Solids Content	48.5 - 49.5 %	48.5 - 49.5 %	
Particle Size	0.20 µm	0.20 µm	
pH	4.0 - 5.0	4.0 - 5.0	
Brookfield Viscosity	<= 800 cP	<= 800 cP	#20/200

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	20.0 °C	68.0 °F	

Descriptive Properties	Value	Comments
Emulsifiers	Anionic	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China