

## Malvern Minerals Sliastic 740 with 33% Novacite® Daper Quartz Filler

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone , Silicone Rubber

**Material Notes:**

Press Vulcanized 5 minutes at 260° F. Product data demonstrates the effect of the Novacite® filler. Information provided by Malvern Minerals Company.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Malvern-Minerals-Sliastic-740-with-33-Novacite-Daper-Quartz-Filler.php](http://www.lookpolymers.com/polymer_Malvern-Minerals-Sliastic-740-with-33-Novacite-Daper-Quartz-Filler.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	Post oven cured 24 hours at 480°F
	52	52	Oven cured 4 hours at 480°F
Tensile Strength at Break	3.52 MPa	510 psi	Oven cured 4 hours at 480°F
	5.17 MPa	750 psi	Post oven cured 24 hours at 480°F
Elongation at Break	260 %	260 %	Oven cured 4 hours at 480°F
	300 %	300 %	Post oven cured 24 hours at 480°F
Tear Strength	8.41 kN/m	48.0 pli	Die B
	8.77 kN/m	50.0 pli	Die B
Compression Set	4.5 %	4.5 %	Post oven cured 24 hours at 480°F
	@Temperature 177 °C, Time 79200 sec	@Temperature 350 °F, Time 22.0 hour	
	15 %	15 %	Oven cured 4 hours at 480°F
	@Temperature 177 °C, Time 79200 sec	@Temperature 350 °F, Time 22.0 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China