

MarkeTech Repton 314 Mullite

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Brand 314 features: Superior hot creep.REPTON setter tiles, kiln furniture, and special fixtures are lightweight, ridge, and high strength ceramics that resist distortion and spalling, even when thermal cycled many times. They are available with a smooth or a unique textured surface that permits pinpoint contact with the load. Sticking can be eliminated as well as providing a surface that breathes, allowing gasses from the ceramic to escape.Applications include firing ceramic capacitors, SOFCs, PZTs, hard and soft ferrites, co-fired substrates and powdered metals. REPTON is available in a wide range of compositions that include a range of alumina, mullite/alumina, zirconia, cordierite, magnesia, and aluminum titanate.

Order this product through the following link:

http://www.lookpolymers.com/polymer_MarkeTech-Repton-314-Mullite.php

Physical Properties	Metric	English	Comments
Bulk Density	2.60 g/cc	0.0939 lb/in ³	
Density	3.61 g/cc	0.130 lb/in ³	calculated from bulk density after subtracting pore volume
Porosity	28 %	28 %	

Mechanical Properties	Metric	English	Comments
Flexural Strength	>= 13.0 MPa	>= 1890 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	4.20 $\mu\text{m}/\text{m}\cdot\text{C}^\circ$	2.33 $\mu\text{in}/\text{in}\cdot\text{F}^\circ$	
	@Temperature 300 C°	@Temperature 572 F°	
	6.00 $\mu\text{m}/\text{m}\cdot\text{C}^\circ$	3.33 $\mu\text{in}/\text{in}\cdot\text{F}^\circ$	
	@Temperature 900 C°	@Temperature 1650 F°	

Component Elements Properties	Metric	English	Comments
Al2O3	93 %	93 %	
SiO2	7.0 %	7.0 %	

Descriptive Properties	Value	Comments
Spall Resist	600 C°	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China