

## MarkeTech Zirconium Oxide Ceramic - Zirconia, Y2O3 Stabilized

Category: Ceramic, Oxide, Zirconium Oxide

## **Material Notes:**

Data provided by the supplier, MarkeTech International. Zirconium oxide is widely used and has superior high temperature properties. When combined with yttria the strength and fracture toughness is significantly improved. This makes some grades of zirconia superior to most materials for abrasion and wear resistance. Parts can be machined before firing in the green state and after firing to meet exacting specifications. Zirconia is electrically conductive above 900°C. Zirconia can be tape cast into very thin sheets for fuel cells and engineered ceramics.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_MarkeTech-Zirconium-Oxide-Ceramic-Zirconia-Y203-Stabilized.php

Physical Properties	Metric	English	Comments
Density	6.60 g/cc	0.238 lb/in³	

Mechanical Properties	Metric	English	Comments
Modulus of Elasticity	160 GPa	23200 ksi	
Flexural Strength	270 MPa	39200 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	10.5 Âμm/m-°C	5.83 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Thermal Conductivity	2.20 W/m-K	15.3 BTU-in/hr-ft²- °F	
Maximum Service Temperature, Air	2400 °C	4350 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China