

## Materion Beryllium Copper Alloy 10 Wire; HT (TH04) Temper; 1.3-12.7 mm Diameter (UNS C17500)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

### Material Notes:

Treatment required for max strength: 2 hrs @ 480-495°C or Mill Hardened Tabulated properties apply to products after age hardening.

Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Materion-Beryllium-Copper-Alloy-10-Wire-HT-TH04-Temper-13-127-mm-Diameter-UNS-C17500.php](http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-10-Wire-HT-TH04-Temper-13-127-mm-Diameter-UNS-C17500.php)

| Physical Properties | Metric    | English                  | Comments |
|---------------------|-----------|--------------------------|----------|
| Density             | 8.83 g/cc | 0.319 lb/in <sup>3</sup> |          |

| Mechanical Properties      | Metric        | English             | Comments |
|----------------------------|---------------|---------------------|----------|
| Tensile Strength, Ultimate | 750 - 970 MPa | 109000 - 141000 psi |          |
| Tensile Strength, Yield    | 650 - 870 MPa | 94300 - 126000 psi  |          |
| Elongation at Break        | >= 10 %       | >= 10 %             |          |
| Modulus of Elasticity      | 138 GPa       | 20000 ksi           |          |

| Thermal Properties   | Metric                     | English                            | Comments |
|----------------------|----------------------------|------------------------------------|----------|
| CTE, linear          | 18.0 µm/m-°C               | 10.0 µin/in-°F                     |          |
|                      | @Temperature 20.0 - 200 °C | @Temperature 68.0 - 392 °F         |          |
| Thermal Conductivity | 200 W/m-K                  | 1390 BTU-in/hr-ft <sup>2</sup> -°F |          |
| Melting Point        | 1010 - 1050 °C             | 1850 - 1920 °F                     |          |
| Solidus              | 1010 °C                    | 1850 °F                            |          |
| Liquidus             | 1050 °C                    | 1920 °F                            |          |

| Component Elements Properties | Metric        | English       | Comments   |
|-------------------------------|---------------|---------------|------------|
| Beryllium, Be                 | 0.40 - 0.70 % | 0.40 - 0.70 % |            |
| Cobalt, Co                    | 2.4 - 2.7 %   | 2.4 - 2.7 %   |            |
| Copper, Cu                    | 97 %          | 97 %          | as balance |

| Electrical Properties  | Metric                            | English                           | Comments                 |
|------------------------|-----------------------------------|-----------------------------------|--------------------------|
| Electrical Resistivity | 0.00000290 -<br>0.00000360 ohm-cm | 0.00000290 -<br>0.00000360 ohm-cm | 48-60% IACS Conductivity |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China