

## Materion Beryllium Copper Alloy 165 Plate & Rolled Bar; H (TD04) Temper; over 51 to 76 mm Thickness (UNS C17000)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

### Material Notes:

Treatment required for max strength: as supplied  
Tabulated properties apply to products after age hardening. Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Materion-Beryllium-Copper-Alloy-165-Plate-Rolled-Bar-H-TD04-Temper-over-51-to-76-mm-Thickness-UNS-C17000.php](http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-165-Plate-Rolled-Bar-H-TD04-Temper-over-51-to-76-mm-Thickness-UNS-C17000.php)

Physical Properties	Metric	English	Comments
Density	8.41 g/cc	0.304 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	88 - 101	88 - 101	
Tensile Strength, Ultimate	580 - 830 MPa	84100 - 120000 psi	
Tensile Strength, Yield	510 - 730 MPa	74000 - 106000 psi	
Elongation at Break	8.0 - 20 %	8.0 - 20 %	
Modulus of Elasticity	131 GPa	19000 ksi	
Machinability	20 %	20 %	

Thermal Properties	Metric	English	Comments
CTE, linear	17.0 $\mu\text{m/m-}^\circ\text{C}$ @Temperature 20.0 - 200 $^\circ\text{C}$	9.44 $\mu\text{in/in-}^\circ\text{F}$ @Temperature 68.0 - 392 $^\circ\text{F}$	
Thermal Conductivity	105 W/m-K	729 BTU-in/hr-ft <sup>2</sup> - $^\circ\text{F}$	
Melting Point	870 - 980 $^\circ\text{C}$	1600 - 1800 $^\circ\text{F}$	
Solidus	870 $^\circ\text{C}$	1600 $^\circ\text{F}$	
Liquidus	980 $^\circ\text{C}$	1800 $^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	1.6 - 1.79 %	1.6 - 1.79 %	
Co + Ni	$\geq 0.20$ %	$\geq 0.20$ %	
Co + Ni + Fe			

Component Elements Properties	<b>&lt;= 0.60 %</b> Metric	<b>&lt;= 0.60 %</b> English	Comments
Copper, Cu	98 %	98 %	as balance

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000910 - 0.0000115 ohm-cm	0.00000910 - 0.0000115 ohm-cm	15-19% IACS Conductivity

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China