

## Materion Beryllium Copper Alloy 190 Strip; AM (TM00) Temper (UNS C17200)

Category : Metal , Nonferrous Metal , Beryllium Alloy , Copper Alloy

### Material Notes:

Treatment required for max strength: Mill Hardened Stress Relaxation-% Stress Remaining after 1000 hrs @ 100°C: 97% Stress Relaxation after 1000 hrs @ 200°C: 67% Formability Ratio, 90° Bend, Radius/Thickness (Good Way): 0 Formability Ratio (bad Way): 0 Superficial Hardness: 30N 37-44 Tabulated properties apply to products after age hardening. Information supplied by Brush Wellman. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Materion-Beryllium-Copper-Alloy-190-Strip-AM-TM00-Temper-UNS-C17200.php](http://www.lookpolymers.com/polymer_Materion-Beryllium-Copper-Alloy-190-Strip-AM-TM00-Temper-UNS-C17200.php)

Physical Properties	Metric	English	Comments
Density	8.36 g/cc	0.302 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	>= 95	>= 95	
Hardness, Rockwell C	<= 23	<= 23	
Hardness, Vickers	210 - 251	210 - 251	
Tensile Strength, Ultimate	680 - 760 MPa	98600 - 110000 psi	
Tensile Strength, Yield	480 - 660 MPa	69600 - 95700 psi	
Elongation at Break	16 - 30 %	16 - 30 %	
Modulus of Elasticity	131 GPa	19000 ksi	
Fatigue Strength	280 - 310 MPa @# of Cycles 1.00e+8	40600 - 45000 psi @# of Cycles 1.00e+8	Reverse Bending (R=1)

Thermal Properties	Metric	English	Comments
CTE, linear	17.0 Åµm/m-Å°C	9.44 Åµin/in-Å°F	
	@Temperature 20.0 - 200 Å°C	@Temperature 68.0 - 392 Å°F	
Thermal Conductivity	105 W/m-K	729 BTU-in/hr-ft <sup>2</sup> -Å°F	
Melting Point	870 - 980 Å°C	1600 - 1800 Å°F	
Solidus	870 Å°C	1600 Å°F	
Liquidus	980 Å°C	1800 Å°F	

Component Elements Properties	Metric	English	Comments
Beryllium, Be	1.8 - 2.0 %	1.8 - 2.0 %	
Co + Ni	>= 0.20 %	>= 0.20 %	
Co + Ni + Fe	<= 0.60 %	<= 0.60 %	
Copper, Cu	98 %	98 %	as balance
Lead, Pb	<= 0.020 %	<= 0.020 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000610 - 0.0000101 ohm-cm	0.00000610 - 0.0000101 ohm-cm	17-28% IACS Conductivity

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China