

## Materion Brush 1915,ç Hard Temper Rod, 0.050" - 0.375"

Category : Metal , Nonferrous Metal , Copper Alloy

### Material Notes:

Information supplied by Brush Wellman Engineered Materials. Treatment required for max strength: as supplied. Brush 1915,ç is Brush Wellman's new heat-treatable leaded copper alloy. Engineered specifically for automatic screw machine applications, Brush 1915 provides high strength and good machinability. Brush Wellman's quality system provides an excellent surface finish, close diameter control, and tight compositional control in Brush 1915. The properties of brush 1915 make it an ideal material for machined electrical contacts. Brush Engineered Materials Inc. changed its name to Materion Corporation in March 2011.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Materion-Brush-1915-Hard-Temper-Rod-0050-0375.php](http://www.lookpolymers.com/polymer_Materion-Brush-1915-Hard-Temper-Rod-0050-0375.php)

Physical Properties	Metric	English	Comments
Density	8.88 g/cc	0.321 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	380 - 510 MPa	55100 - 74000 psi	
Tensile Strength, Yield	310 - 480 MPa	45000 - 69600 psi	
Elongation at Break	5.0 - 20 %	5.0 - 20 %	
Modulus of Elasticity	124 GPa	18000 ksi	
Machinability	75 %	75 %	

Thermal Properties	Metric	English	Comments
CTE, linear	17.7 $\mu\text{m/m-}^\circ\text{C}$ @Temperature 20.0 - 200 $^\circ\text{C}$	9.83 $\mu\text{in/in-}^\circ\text{F}$ @Temperature 68.0 - 392 $^\circ\text{F}$	
Thermal Conductivity	210 W/m-K	1460 BTU-in/hr-ft <sup>2</sup> - $^\circ\text{F}$	
Melting Point	1038 - 1082 $^\circ\text{C}$	1900 - 1980 $^\circ\text{F}$	
Solidus	1038 $^\circ\text{C}$	1900 $^\circ\text{F}$	
Liquidus	1082 $^\circ\text{C}$	1980 $^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Copper, Cu	98 %	98 %	as balance
Lead, Pb	0.50 - 1.0 %	0.50 - 1.0 %	

<small>Nickel Ni</small> Component Elements Properties	<small>0.80 - 1.2 %</small> Metric	<small>0.80 - 1.2 %</small> English	Comments
Phosphorous, P	0.15 - 0.35 %	0.15 - 0.35 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000310 ohm-cm	0.00000310 ohm-cm	(55% IACS Conductivity)

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China