

Meehanite HE Heat Resisting Cast Iron

Category : Metal , Ferrous Metal , Cast Iron

Material Notes:

Type HE is a freely machinable material in the as-cast condition. Withstands rapid heating and cooling without premature failure, offers good dimensional stability and a good range of strength properties. Recommended for ingot molds, slag pots, hot plates, and parts heated rapidly by a naked flame. General Meehanite information - Meehanite metal is first melted to a definite degree of undercooling or constitution which is related to the section of the casting to be poured and the range of physical properties such as tensile strength and hardness required. Nucleation with patented mixtures of graphitizing agents results in the removal of undercooling, in the controlled precipitation of graphite and in a fine grained eutectic cell structure which determines the density and physical integrity of the casting. Ordinary cast irons made to chemical specifications which do not include the benefit of controlled undercooling are influenced by mass effect to a maximum degree and for this and other reasons cannot be considered an equivalent to Meehanite metal. Information provided by Meehanite Marketing Association.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Meehanite-HE-Heat-Resisting-Cast-Iron.php

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	170	170	Nominal
Tensile Strength, Ultimate	172 MPa	25000 psi	
Modulus of Elasticity	68.9 GPa	10000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	12.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	6.66 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 37.8 - 538 $\text{Å}^\circ\text{C}$	@Temperature 100 - 1000 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	42.9 W/m-K	298 BTU-in/hr-ft $^2\cdot\text{Å}^\circ\text{F}$	
	@Temperature 10.0 - 232 $\text{Å}^\circ\text{C}$	@Temperature 50.0 - 450 $\text{Å}^\circ\text{F}$	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China