

Micropol Microlin LL17 Linear Polyethylene Rotational Molding Powder

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Rotational Molding Grade

Material Notes:

Information provided by Micropol Limited

Order this product through the following link:

http://www.lookpolymers.com/polymer_Micropol-Microlin-LL17-Linear-Polyethylene-Rotational-Molding-Powder.php

Physical Properties	Metric	English	Comments
Density	0.924 g/cc	0.0334 lb/in ³	ASTM D792
Melt Flow	4.0 - 6.0 g/10 min	4.0 - 6.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	10.0 MPa	1450 psi	50mm/min; ASTM D638-64T
Elongation at Break	840 %	840 %	ASTM D638-64T
Flexural Modulus	0.245 GPa	35.5 ksi	ASTM D760-66

Thermal Properties	Metric	English	Comments
Vicat Softening Point	91.0 Â°C	196 Â°F	ASTM D1525
Brittleness Temperature	<= -70.0 Â°C	<= -94.0 Â°F	ASTM D746
Flammability, UL94	V-2	V-2	
Oxygen Index	26 %	26 %	Critical

Descriptive Properties	Value	Comments
British Standard 2782:508A	Zero Burn Rate	
British Standard 476 Part 7	Class 2	
Civil Aviation Authority Spec No 8 Vertical Test	Pass	
Stores Materials Container Fire Test	Pass	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China