

Mitsubishi Iupilon® E2001R 5 MFI FDA Compliant Polycarbonate With Release

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded

Material Notes:

Information provided by US distributor Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mitsubishi-Iupilon-E2001R-5-MFI-FDA-Compliant-Polycarbonate-With-Release.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ASTM D792
Water Absorption	0.25 %	0.25 %	24 hours at 73°F
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	ASTM D955
Melt Flow	5.0 g/10 min @Load 1.20 kg, Temperature 300 °C	5.0 g/10 min @Load 2.65 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	65	65	ASTM D785
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Ultimate	68.5 MPa @Thickness 3.17 mm	9940 psi @Thickness 0.125 in	
Tensile Strength, Yield	60.3 MPa @Thickness 3.17 mm	8750 psi @Thickness 0.125 in	
Elongation at Break	120 % @Thickness 3.17 mm	120 % @Thickness 0.125 in	
Flexural Yield Strength	89.1 MPa @Thickness 3.17 mm	12900 psi @Thickness 0.125 in	
Flexural Modulus	2.25 GPa @Thickness 3.17 mm	326 ksi @Thickness 0.125 in	
Izod Impact, Notched	9.77 J/cm @Thickness 3.17 mm	18.3 ft-lb/in @Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
	117 Åµm/m-Å°C	65.0 Åµin/in-Å°F	

CTE linear Thermal Properties	Metric @ Temperature 20.0 Â°C	English @ Temperature 68.0 Â°F	ASTM D696 Comments
Deflection Temperature at 0.46 MPa (66 psi)	140 Â°C	284 Â°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	128 Â°C	262 Â°F	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0625 in	

Optical Properties	Metric	English	Comments
Refractive Index	1.585	1.585	nD
Transmission, Visible	87 %	87 %	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	288 - 304 Â°C	550 - 580 Â°F	
Middle Barrel Temperature	299 - 321 Â°C	570 - 610 Â°F	
Front Barrel Temperature	316 - 338 Â°C	600 - 640 Â°F	
Nozzle Temperature	304 - 332 Â°C	580 - 630 Â°F	
Melt Temperature	316 - 343 Â°C	600 - 650 Â°F	
Mold Temperature	82.2 - 116 Â°C	180 - 240 Â°F	
Drying Temperature	121 Â°C	250 Â°F	
Dry Time	3 - 4 hour	3 - 4 hour	48 hours max.
Injection Pressure	110 - 152 MPa	16000 - 22000 psi	
Back Pressure	0.345 - 1.38 MPa	50.0 - 200 psi	
Clamp Pressure	27.6 - 68.9 MPa	4000 - 10000 psi	
Shot Size	40 - 60 %	40 - 60 %	
Screw Speed	40 - 70 rpm	40 - 70 rpm	

Descriptive Properties	Value	Comments
Injection Speed- Edge Gate	Slow to Medium	
Injection Speed- Tab Gate	Medium to Fast	
Injection Speed- Tunnel Gate	Fast	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China