

Mitsui Arlenâ„ç A335 35% Glass Fiber-Reinforced Modified Nylon 6T (COND)

Category : Polymer , Thermoplastic , Nylon

Material Notes:

ARLENâ„ç is a heat resistant, modified polyamide 6T developed by Mitsui Chemicals, Inc. With a high melting point (320Â°C) and a rigidity level comparable to super engineering plastics, it possesses strong dimensional stability and chemical resistance. In addition, the effect of water absorption, which is a traditional weakness of polyamides, has been reduced to a minimum. Applications: Cylinder head coversThermostat casesOil pump housingsHydraulic system pistonsCooling system partsRoller/pulley partsInformation provided by Mitsui.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mitsui-Arlen-A335-35-Glass-Fiber-Reinforced-Modified-Nylon-6T-COND.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/inÂ³	ASTM D792
Filler Content	35 %	35 %	
Water Absorption	0.30 % @Thickness 2.00 mm	0.30 % @Thickness 0.0787 in	24 hours in 23Â°C water; ASTM D570
	1.8 % @Thickness 2.00 mm	1.8 % @Thickness 0.0787 in	24 hours in 100Â°C water; ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 2.00 mm	0.0030 in/in @Thickness 0.0787 in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0060 cm/cm @Thickness 2.00 mm	0.0060 in/in @Thickness 0.0787 in	Vertical Direction; ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	220 MPa	31900 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	Measured between the chucks; ASTM D638
Flexural Strength	320 MPa	46400 psi	ASTM D790
Flexural Modulus	11.0 GPa	1600 ksi	ASTM D790
Izod Impact, Notched	1.50 J/cm	2.81 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	45.0 Âµm/m-Â°C @Temperature 20.0	25.0 Âµin/in-Â°F	Vertical Direction; ASTM D696

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 $\text{Å}^\circ\text{C}$	11.1 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 $\text{Å}^\circ\text{F}$	ASTM D696
Melting Point	320 $\text{Å}^\circ\text{C}$	608 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 1.8 MPa (264 psi)	310 $\text{Å}^\circ\text{C}$	590 $\text{Å}^\circ\text{F}$	ASTM D648
Glass Transition Temp, Tg	125 $\text{Å}^\circ\text{C}$	257 $\text{Å}^\circ\text{F}$	
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Feed Temperature	50.0 - 90.0 $\text{Å}^\circ\text{C}$	122 - 194 $\text{Å}^\circ\text{F}$	Hopper Bottom Temp for Mechanical and Structural Standard Molding
	50.0 - 90.0 $\text{Å}^\circ\text{C}$	122 - 194 $\text{Å}^\circ\text{F}$	Hopper Bottom for Electronic and Electric Standard Molding
Nozzle Temperature	315 - 335 $\text{Å}^\circ\text{C}$	599 - 635 $\text{Å}^\circ\text{F}$	NH Cylinder Temp for Electronic and Electric Standard Molding
	325 - 340 $\text{Å}^\circ\text{C}$	617 - 644 $\text{Å}^\circ\text{F}$	NH Cylinder Temp for Mechanical and Structural Standard Molding
Zone 1	300 - 325 $\text{Å}^\circ\text{C}$	572 - 617 $\text{Å}^\circ\text{F}$	C1 Cylinder Temp for Electronic and Electric Standard Molding
	315 - 330 $\text{Å}^\circ\text{C}$	599 - 626 $\text{Å}^\circ\text{F}$	C1 Cylinder Temp for Mechanical and Structural Standard Molding
Zone 2	315 - 335 $\text{Å}^\circ\text{C}$	599 - 635 $\text{Å}^\circ\text{F}$	C2 Cylinder Temp for Electronic and Electric Standard Molding
	320 - 335 $\text{Å}^\circ\text{C}$	608 - 635 $\text{Å}^\circ\text{F}$	C2 Cylinder Temp for Mechanical and Structural Standard Molding
Zone 3	320 - 335 $\text{Å}^\circ\text{C}$	608 - 635 $\text{Å}^\circ\text{F}$	C3 Cylinder Temp for Electronic and Electric Standard Molding
	325 - 340 $\text{Å}^\circ\text{C}$	617 - 644 $\text{Å}^\circ\text{F}$	C3 Cylinder Temp for Mechanical and Structural Standard Molding
Mold Temperature	90.0 - 140 $\text{Å}^\circ\text{C}$	194 - 284 $\text{Å}^\circ\text{F}$	for Mechanical and Structural Standard Molding
	90.0 - 140 $\text{Å}^\circ\text{C}$	194 - 284 $\text{Å}^\circ\text{F}$	for Electronic and Electric Standard Molding
Screw Speed	150 rpm	150 rpm	for Mechanical and Structural Standard Molding
	150 rpm	150 rpm	for Electronic and Electric Standard Molding

Descriptive Properties	Value	Comments
Injection Pressure	Medium	Electronic and Electric Standard Molding
	Medium	Mechanical and Structural Standard Molding
Injection Speed	Medium	Electronic and Electric Standard Molding
	Medium	Mechanical and Structural Standard Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China