

Momentive Performance Materials HTR1004 PBN/PG Heating Element

Category : Carbon , Graphite , Ceramic , Nitride

Material Notes:

PBN/PG resistance heating elements combine the unique electrical, chemical, and thermal properties of PBN, a dielectric material, and Pyrolytic Graphite (PG), an electrical conductor, to produce a truly advanced heating system. These non-brittle refractory materials owe their exceptional purity to the high temperature, chemical vapor deposition (CVD) production method. The high thermal conductivity and anisotropy of both materials result in excellent thermal uniformity. Performance Advantages: PBN/PG "printed circuit" heaters utilize PBN as an insulating substrate and Pyrolytic Graphite as the resistive element. This combination of unique materials delivers performance advantages not available in conventional thermal systems. Operating temperatures to 1800° C. Superior performance in ultra high vacuum. Chemically inert to most corrosive gases, liquids. Unaffected by most molten metals. Long life, dimensionally and electrically stable. High resistance for low cost power supplies. Mechanically durable, thermally shock resistant. Unaffected by vibration. Tailored thermal gradients for specific requirements. Wide range of resistance values to match existing supplies. Ultra-fast response, low thermal mass. Power outputs over 50 watts/cm² (325 watts/in²). Dielectric, fully dense, ceramic surface. Information provided by Momentive Performance Materials, formerly GE Advanced Ceramics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Momentive-Performance-Materials-HTR1004-PBNPG-Heating-Element.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1800 Â°C	3270 Â°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000250 ohm-cm	0.000250 ohm-cm	
	@Temperature 1000 Â°C	@Temperature 1830 Â°F	
	0.000520 ohm-cm	0.000520 ohm-cm	
	@Temperature 0.000 Â°C	@Temperature 32.0 Â°F	

Descriptive Properties	Value	Comments
Contacts	M4 thread in post end	
Maximum Current	11	Outer
	13	Inner
Pattern Diameter	100 mm	
Power Rating	1000 Watts	Outer
	1150 Watts	Inner

Thickness

Descriptive Properties	5 mm Value	Comments
Voltage at Power Rating	110 Volts	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China