

## Momentive Performance Materials PolarTherm® PT160 Boron Nitride (BN) Powder

Category: Ceramic, Nitride, Other Engineering Material, Additive/Filler for Polymer

## **Material Notes:**

Fine Hexagonal BN PowderWhen used in a variety of polymeric materials, PolarTherm™'s heat dissipating capability helps extend the service life and enhance the reliability of electronic components and assemblies.Information provided by Momentive Performance Materials, formerly GE Advanced Ceramics.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Momentive-Performance-Materials-PolarTherm-PT160-Boron-Nitride-BN-Powder.php

| Physical Properties   | Metric        | English       | Comments    |
|-----------------------|---------------|---------------|-------------|
| Density               | 2.25 g/cc     | 0.0813 lb/in³ | Theoretical |
| Particle Size         | 6.0 - 12 μm   | 6.0 - 12 µm   | average     |
| Specific Surface Area | 8.0 - 15 m²/g | 8.0 - 15 m²/g |             |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|--------|---------|----------|
| Hardness, Knoop       | 11     | 11      |          |

| Thermal Properties     | Metric               | English                          | Comments |
|------------------------|----------------------|----------------------------------|----------|
| CTE, linear            | <= 1.00 μm/m-°C      | <= 0.556 μin/in-°F               |          |
|                        | @Temperature 20.0 °C | @Temperature 68.0 °F             |          |
| Specific Heat Capacity | 0.794 J/g-°C         | 0.190 BTU/lb-°F                  |          |
| Thermal Conductivity   | 266 - 284 W/m-K      | 1850 - 1970 BTU-in/hr-<br>ft²-°F |          |

| Electrical Properties  | Metric             | English            | Comments |
|------------------------|--------------------|--------------------|----------|
| Electrical Resistivity | 1.00e+15 ohm-cm    | 1.00e+15 ohm-cm    |          |
| Dielectric Constant    | 3.9                | 3.9                |          |
| Dissipation Factor     | <= 0.00020         | <= 0.00020         |          |
|                        | @Frequency 1e+6 Hz | @Frequency 1e+6 Hz |          |

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China