

## Monmouth Rubber & Plastics Durafoamâ, ¢ P392SHD EPDM

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

## **Material Notes:**

Note 1: The Durafoamâ,¢100% EPDM Series, Expanded Cellular Rubber Sheets, were tested for QUV Ultraviolet Light Exposure. Test specimens for each stock number were cut 3 inches by 11 inches from ¼ inch thick sheets. These test pieces were exposed for 120 hours to a cycle consisting of: 1. Light at 70°C for 8 hours 2. Dark at 50°C for 4 hours 3. Condensation Cooling for 15 minutesInformation provided by Monmouth Rubber & Plastics Corp.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Monmouth-Rubber-Plastics-Durafoam-P392SHD-EPDM.php

| Physical Properties   | Metric         | English        | Comments   |
|-----------------------|----------------|----------------|------------|
| Density               | 0.240 g/cc     | 0.00868 lb/in³ |            |
| Water Absorption      | <= 1.0 %       | <= 1.0 %       | ASTM D1056 |
| Linear Mold Shrinkage | <= 0.017 cm/cm | <= 0.017 in/in | Note 1     |

| Mechanical Properties | Metric              | English         | Comments |
|-----------------------|---------------------|-----------------|----------|
| Tensile Strength      | >= 1.03 MPa         | >= 150 psi      |          |
| Elongation at Break   | >= 200 %            | >= 200 %        |          |
| Compressive Strength  | 0.0621 - 0.0896 MPa | 9.00 - 13.0 psi | 0.25     |
| Compression Set       | <= 25 <b>%</b>      | <= 25 <b>%</b>  | B2 – 50% |

| Thermal Properties               | Metric   | English  | Comments |  |
|----------------------------------|----------|----------|----------|--|
| Maximum Service Temperature, Air | -62.2 °C | -80.0 °F |          |  |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| Color                  | Grey  |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Address: United North Road 215, Fengxian District, Shanghai City, China

Skype : lookpolymers