

Multibase Multi-ABS 3525 Black

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Moisture content is 0.08%.Data provided by Multibase.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-ABS-3525-Black.php

Physical Properties	Metric	English	Comments
Melt Flow	5.8 g/10 min @Load 3.80 kg, Temperature 230 °C	5.8 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D-1238-94a

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	37.5 MPa	5440 psi	ASTM D638-95
Elongation at Break	35.3 %	35.3 %	ASTM D638-95
Flexural Strength	60.0 MPa	8700 psi	ASTM D790-95
Flexural Modulus	2.232 GPa	323.7 ksi	Method 1, Proc. B; ASTM D-790-95
Izod Impact, Notched	1.23 J/cm	2.30 ft-lb/in	ASTM D256-93a
Gardner Impact	1.80 J	1.33 ft-lb	ASTM D5420-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China