

Multibase Multi-Flamâ„ç 2602 PP Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Features:Flame RetardantHalogenatedBlooming, None Forms:PelletsProcessing Methods:Injection MoldingInformation provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flam-2602-PP-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in ³	ASTM D792
Melt Flow	2.0 g/10 min @Load 2.16 kg, Temperature 230 Â°C	2.0 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	17.2 MPa	2500 psi	ASTM D638
Elongation at Break	990 %	990 %	ASTM D638
Flexural Modulus	0.503 GPa	73.0 ksi	ASTM D790
Izod Impact, Notched	6.41 J/cm	12.0 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-2	V-2	0.125 in

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China