

## Multibase Multi-Flex<sup>®</sup> 1047-2000 TPO Thermoplastic Polyolefin Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyolefin

### Material Notes:

Features: Chemical Resistance, Good Paintable Ozone Resistant Thermal Stability, Good Density, Low Tear Strength, Good Forms: Pellets Processing Method: Injection Molding Uses: Automotive Applications Information provided by Multibase

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Flex-1047-2000-TPO-Thermoplastic-Polyolefin-Elastomer.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-1047-2000-TPO-Thermoplastic-Polyolefin-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.892 g/cc	0.892 g/cc	ASTM 792
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	ASTM D955
Melt Flow	3.0 g/10 min @Load 2.16 kg, Temperature 230 °C	3.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	45	45	10 seconds; ASTM D2240
Tensile Strength, Yield	12.8 MPa	1850 psi	Elastic; ASTM D412
Elongation at Break	680 %	680 %	Elastic; ASTM D412
Flexural Modulus	0.324 GPa	47.0 ksi	ASTM D790
Tear Strength	98.2 kN/m	560 pli	ASTM D624

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	177 - 199 °C	350 - 390 °F	
Middle Barrel Temperature	199 - 221 °C	390 - 430 °F	
Front Barrel Temperature	221 - 232 °C	430 - 450 °F	
Nozzle Temperature	6.11 - 232 °C	43.0 - 450 °F	
Mold Temperature	37.8 °C	100 °F	

Descriptive Properties	Value	Comments
Clamp Tonnage	2-4 tons/in <sup>2</sup>	
Screw L/D Ratio	20:1	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**