

Multibase Multi-Flex[®] A 5541 Clear TPE Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer , TPE

Material Notes:

Forms: Pellets Processing Methods: Injection Molding Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-A-5541-Clear-TPE-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.892 g/cc	0.892 g/cc	ASTM 792
Linear Mold Shrinkage	0.00010 cm/cm	0.00010 in/in	ASTM D955
Melt Flow	128 g/10 min @Load 2.16 kg, Temperature 230 °C	128 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	10 seconds; ASTM D2240
Tensile Strength, Yield	2.12 MPa	307 psi	Elastic; ASTM D412
Elongation at Break	700 %	700 %	Elastic; ASTM D412
Tear Strength	35.1 kN/m	200 pli	ASTM D624

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	clear; thickness not quantified

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China