

Multibase Multi-Flex[®] G 7430 TPE Styrene Ethylene Butylene Styrene Block Copolymer

Category : Polymer , Thermoplastic

Material Notes:

Forms: Pellets Processing Methods: Injection Molding Information provided by Multibase

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-G-7430-TPE-Styrene-Ethylene-Butylene-Styrene-Block-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.942 g/cc	0.942 g/cc	ASTM 792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72	72	10 seconds; ASTM D2240
Tensile Strength, Yield	12.8 MPa	1850 psi	Elastic; ASTM D412
Elongation at Break	750 %	750 %	Elastic; ASTM D412
Tear Strength	29.8 kN/m	170 pli	ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China