

## Multibase Multi-Flex<sup>®</sup> G 7715 TPE Styrene Ethylene Butylene Styrene Block Copolymer

Category : Polymer , Thermoplastic

**Material Notes:**

Forms: Pellets Processing Methods: Injection Molding Information provided by Multibase

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Flex-G-7715-TPE-Styrene-Ethylene-Butylene-Styrene-Block-Copolymer.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-G-7715-TPE-Styrene-Ethylene-Butylene-Styrene-Block-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	ASTM 792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	57	57	10 seconds; ASTM D2240
Tensile Strength, Yield	11.7 MPa	1700 psi	Elastic; ASTM D412
Elongation at Break	750 %	750 %	Elastic; ASTM D412
Tear Strength	26.3 kN/m	150 pli	ASTM D624

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China