

## Multibase Multi-Flex® TPE A 7301 BLK

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

### Material Notes:

The data is the actual data obtained from the above sample. This material is based on Shell's Kraton G technology. Multi-Flex TPE contains Kraton™ G.Data provided by Multibase.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Flex-TPE-A-7301-BLK.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-7301-BLK.php)

Physical Properties	Metric	English	Comments
Density	0.997 g/cc	0.0360 lb/in <sup>3</sup>	ASTM D792
Melt Flow	2.35 g/10 min	2.35 g/10 min	(Condition L) ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72	72	10 sec; ASTM D-2240
Tensile Strength, Ultimate	8.80 MPa	1280 psi	ASTM D412
Elongation at Break	795 %	795 %	ASTM D412
Tear Strength	41.2 kN/m	235 pli	ASTM D624
Compression Set	30 %	30 %	for 168 hours at 25°C; ASTM 395

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China