

## Multibase Multi-Flex® TPE A 7606 JA6A BLK

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

### Material Notes:

The burn rate is 1.2 in/min (30 mm/min) based on ASTM FM VSS 302. Multi-Flex TPE contains Kraton™ G. Data provided by Multibase.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Multibase-Multi-Flex-TPE-A-7606-JA6A-BLK.php](http://www.lookpolymers.com/polymer_Multibase-Multi-Flex-TPE-A-7606-JA6A-BLK.php)

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in <sup>3</sup>	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73	73	10 sec; ASTM D-2240
Tensile Strength, Ultimate	>= 7.45 MPa	>= 1080 psi	ASTM D412
Elongation at Break	>= 400 %	>= 400 %	ASTM D412
Tear Strength	>= 38.53 kN/m	>= 219.9 pli	ASTM D624

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China