

Multibase TPSiV™ 3011-85A Thermoplastic Silicone Vulcanizate

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV) , Polyurethane, TP , Silicone, Thermoplastic

Material Notes:

These materials are a novel family of TPV products based on cross-linked silicone rubber dispersed into various engineering thermoplastics. The dispersion of the silicone internal phase is produced by dynamic "vulcanization" or cross-linking of silicone polymers within the thermoplastic organic phase and results in a stable droplet type morphology as shown in the TEM micrograph. TPSiV™ combines the elastomeric performance of silicone rubber with the melt re-processability and thermal and chemical resistance of engineering thermoplastics. Thermoplastic polyurethane based TPSiV™ (3010, 3011, 3111, 3040, 3340 grades) combine the benefits of excellent abrasion resistance from the polyurethane as well as the lower coefficient of friction and improved temperature properties from the silicone rubber. TPSiV™ 3011-50A / 60A / 70A / 85A: General purpose grades designed for both injection molding and extrusion applications. Plasticizer free (except the 50A product), which results in excellent bonding via 2-shot molding or co-extrusion to PC, ABS, PU, and PVC. They display good tensile and tear strength. Information provided by Multibase, a Dow Corning Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Multibase-TPSiV-3011-85A-Thermoplastic-Silicone-Vulcanizate.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	82	82	10 sec; ASTM D2240
Tensile Strength at Break	16.0 MPa	2320 psi	ASTM D412
Elongation at Break	600 %	600 %	ASTM D412
Tear Strength	45.6 kN/m	260 pli	ASTM D412

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	205 °C	401 °F	
Middle Barrel Temperature	210 °C	410 °F	
Front Barrel Temperature	215 °C	419 °F	
Nozzle Temperature	220 °C	428 °F	
Mold Temperature	10.0 - 30.0 °C	50.0 - 86.0 °F	
Drying Temperature	80.0 °C	176 °F	

Processing Properties	Metric ^{ur}	English ^{ur}	Comments
Descriptive Properties		Value	Comments
Injection Rate		Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China