

## Mytex Polymers AS319L-01US Thermoplastic Polyolefin, 19% Talc Filled

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Olefinic Elastomer (TPO) , Polyolefin

### Material Notes:

AS319L-01US is a compounded thermoplastic polyolefin (TPO) designed for exterior automotive applications requiring cold temperature impact, processability and paintability. Available in natural or generic black. Key Applications: Exterior Parts-Bumper Fascia, Cladding OEM Approvals: Chrysler MS-DC 256 Type C, CPN 3338 CP 1120 Information provided by Mytex Polymers

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Mytex-Polymers-AS319L-01US-Thermoplastic-Polyolefin-19-Talc-Filled.php](http://www.lookpolymers.com/polymer_Mytex-Polymers-AS319L-01US-Thermoplastic-Polyolefin-19-Talc-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in <sup>3</sup>	ISO 1183 A
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	48 hours after molding; ISO 294-3/4
	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	48 hours after molding; ISO 294-3/4
	@Temperature 80.0 °C, Time 3600 sec	@Temperature 176 °F, Time 1.00 hour	
	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	48 hours after molding; ISO 294-3/4
	@Temperature 121 °C, Time 3600 sec	@Temperature 250 °F, Time 1.00 hour	
Melt Flow	24 g/10 min	24 g/10 min	ISO 1133 B
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	
Ash	19 %	19 %	ISO 3451/1A
	@Temperature 600 °C	@Temperature 1110 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	17.0 MPa	2470 psi	ISO 527-1/1A/50
Flexural Modulus	1.70 GPa	247 ksi	Chord, 2mm/min; ISO 178
Izod Impact, Unnotched (ISO)	48.0 kJ/m <sup>2</sup>	22.8 ft-lb/in <sup>2</sup>	ISO 180/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Dart Drop, Total Energy	16.0 J	11.8 ft-lb	Multiaxial Impact Strength, Max Load, 2.2 m/s; ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	102 °C	216 °F	Method A, flatwise, unannealed; ISO 75-1/2

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China