

Mytex Polymers AS33L-07V Polypropylene, Rubber modified, Compounded

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Description: AS33L-07 is a compounded, rubber modified polypropylene with good impact and excellent material flow properties. This product is designed for painted and mold-in-color applications. Key Applications: Bumper fascias, cladding and bodyside molding. Information provided by Mytex Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mytex-Polymers-AS33L-07V-Polypropylene-Rubber-modified-Compounded.php

Physical Properties	Metric	English	Comments
Density	0.930 g/cc	0.0336 lb/in ³	ASTM D792
Melt Flow	22 g/10 min	22 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	44	44	ASTM D785
Tensile Strength, Yield	19.0 MPa	2760 psi	50 mm/min; ASTM D638
Flexural Modulus	1.15 GPa	167 ksi	Tangent; 1.3 mm/min; ASTM D790
Izod Impact, Notched	6.00 J/cm @Temperature 23.0 °C	11.2 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	85.0 °C	185 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China