

Mytex Polymers AS33L(W)-06 Polypropylene, Rubber modified, Talc filled, Compounded

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Description: AS33L(W)-06 is a compounded, talc, rubber modified polypropylene for exterior automotive applications. Material has outstanding moldability and excellent balance of high stiffness and good impact performance properties. Key Applications: Automotive exterior, painted or mold-in-color. Information provided by Mytex Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Mytex-Polymers-AS33LW-06-Polypropylene-Rubber-modified-Talc-filled-Compounded.php

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in ³	ASTM D792
Melt Flow	28 g/10 min	28 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	50	50	ASTM D785
Tensile Strength, Yield	20.0 MPa	2900 psi	50 mm/min; ASTM D638
Flexural Modulus	1.40 GPa	203 ksi	Tangent; 1.3 mm/min; ASTM D790
Izod Impact, Notched	5.50 J/cm @Temperature 23.0 °C	10.3 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	100 °C	212 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China