

ND Industries 333 Surface Insensitive Instant Superglue

Category : Polymer , Adhesive , Thermoset

Material Notes:

Low-medium viscosity for difficult to bond substrates

Order this product through the following link:

http://www.lookpolymers.com/polymer_ND-Industries-333-Surface-Insensitive-Instant-Superglue.php

Physical Properties	Metric	English	Comments
Viscosity	250 - 350 cP	250 - 350 cP	

Mechanical Properties	Metric	English	Comments
Shear Strength	20.7 - 24.1 MPa	3000 - 3500 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	82.2 °C	180 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	0.250 - 0.667 min	0.00417 - 0.0111 hour	On Steel (Fixture)
	1440 min	24.0 hour	On Steel (Full)

Descriptive Properties	Value	Comments
Color	Clear	
Gap Fill, in.	0.006	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China