

NIZHNEKAMSKNEFTEKHIM PE 6152C (526H3) High Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts. Information provided by manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_NIZHNEKAMSKNEFTEKHIM-PE-6152C-526H3-High-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.950 - 0.954 g/cc	0.0343 - 0.0345 lb/in ³	Base Resin; ASTM D1505
Melt Flow	0.25 - 0.40 g/10 min	0.25 - 0.40 g/10 min	ASTM D1283/L
	@Load 5.00 kg, Temperature 190 °C	@Load 11.0 lb, Temperature 374 °F	
	5.0 - 8.0 g/10 min	5.0 - 8.0 g/10 min	Flow@21.6kg/Flow@5kg ratio > 20; ASTM D1283
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	>= 55.0 MPa	>= 7980 psi	ASTM D882
Film Tensile Strength at Yield, TD	>= 48.0 MPa	>= 6960 psi	ASTM D882
Film Elongation at Break, MD	>= 450 %	>= 450 %	ASTM D882
Film Elongation at Break, TD	>= 550 %	>= 550 %	ASTM D882
Tensile Modulus	>= 0.800 GPa	>= 116 ksi	2% sec, TD; ASTM D882
	>= 0.900 GPa	>= 131 ksi	2% sec, MD; ASTM D882
Elmendorf Tear Strength, MD	>= 0.512 g/micron	>= 13.0 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	>= 2.36 g/micron	>= 60.0 g/mil	ASTM D1922
Dart Drop Test	>= 150 g	>= 0.331 lb	ASTM D1709

Descriptive Properties	Value	Comments
Gel Content (pcs./m ²)	600	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China