

NOVA Chemicals Sclair® 2907 HDPE Injection Molding Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Injection Molded

Material Notes:

Features: High stiffness, maximum impact strength and toughness, good top loading capability, high surface gloss. Applications: Protective sports equipment, safety helmets, high impact custom molding. Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_NOVA-Chemicals-Sclair-2907-HDPE-Injection-Molding-Resin.php

Physical Properties	Metric	English	Comments
Density	0.960 g/cc	0.0347 lb/in ³	ASTM D792
Environmental Stress Crack Resistance	<= 10 hour	<= 10 hour	F50, Condition A, ASTM D1693, 100% Igepal
Melt Flow	4.9 g/10 min @Load 2.16 kg, Temperature 190 °C	4.9 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	65	65	ASTM D2240
Tensile Strength, Yield	29.0 MPa	4210 psi	ASTM D638
Elongation at Break	1500 %	1500 %	ASTM D638
Flexural Modulus	1.28 GPa	186 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	129 °C	264 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Melt Temperature	170 - 215 °C	338 - 419 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China