

Network Polymers F7000 Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Flame Retardant

Material Notes:

Description: Ignition Retardant Information provided by Network Polymers Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Network-Polymers-F7000-Polystyrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.16 g/cc	1.16 g/cc	ASTM D792
Melt Flow	9.5 g/10 min @Load 5.00 kg, Temperature 200 °C	9.5 g/10 min @Load 11.0 lb, Temperature 392 °F	Procedure A Condition G; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	22.1 MPa	3200 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Flexural Strength	31.0 MPa	4500 psi	ASTM D790
Flexural Modulus	1.72 GPa	250 ksi	ASTM D790
Izod Impact, Notched	1.17 J/cm	2.20 ft-lb/in	Injection Molding; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	82.2 °C	180 °F	ASTM D648
Vicat Softening Point	96.0 °C	205 °F	ASTM D1525
Flammability, UL94	V-0	V-0	0.0625 in

Descriptive Properties	Value	Comments
Color Stability	min 10	Change in E at 300 hours; ASTM D4459

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China