

## Nilit FRIANYL A63 H-GV20 Nylon 6.6 for injection molding, 20% glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled

### Material Notes:

Nylon 6.6 for injection molding, heat stabilized (dark natural color). Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nilit-FRIANYL-A63-H-GV20-Nylon-66-for-injection-molding-20-glass-fiber-reinforced.php](http://www.lookpolymers.com/polymer_Nilit-FRIANYL-A63-H-GV20-Nylon-66-for-injection-molding-20-glass-fiber-reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.26 g/cc	0.0455 lb/in <sup>3</sup>	ISO 1183
Water Absorption	1.5 - 2.2 %	1.5 - 2.2 %	ISO 62
Water Absorption at Saturation	6.0 - 8.0 %	6.0 - 8.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.0050 - 0.014 cm/cm	0.0050 - 0.014 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	165 MPa	23900 psi	ISO 2039-1
Tensile Strength at Break	150 MPa	21800 psi	ISO 527
Elongation at Break	4.5 %	4.5 %	ISO 527
Tensile Modulus	7.00 GPa	1020 ksi	ISO 527
Flexural Strength	190 MPa	27600 psi	ISO 178
Flexural Modulus	6.40 GPa	928 ksi	ISO 178
Charpy Impact Unnotched	3.50 J/cm <sup>2</sup>	16.7 ft-lb/in <sup>2</sup>	DIN 53453
	3.00 J/cm <sup>2</sup> @Temperature -40.0 °C	14.3 ft-lb/in <sup>2</sup> @Temperature -40.0 °F	DIN 53453
Charpy Impact, Notched	0.700 J/cm <sup>2</sup>	3.33 ft-lb/in <sup>2</sup>	DIN 53453
	0.600 J/cm <sup>2</sup> @Temperature -40.0 °C	2.86 ft-lb/in <sup>2</sup> @Temperature -40.0 °F	DIN 53453

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	ISO 3146 DSC

Thermal Properties <small>temperature, Air</small>	Metric	English	Comments <small>; FRISETTA Test Method</small>
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	550 V	550 V	CTI 100; IEC 112

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China