

Nilit FRIANYL A63 H-GV30 Nylon 6.6 for injection molding, 30% glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Nylon 6.6 for injection molding, heat stabilized (dark natural color). Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nilit-FRIANYL-A63-H-GV30-Nylon-66-for-injection-molding-30-glass-fiber-reinforced.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	ISO 1183
Water Absorption	1.4 - 2.4 %	1.4 - 2.4 %	ISO 62
Water Absorption at Saturation	5.0 - 7.0 %	5.0 - 7.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.0050 - 0.014 cm/cm	0.0050 - 0.014 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	180 MPa	26100 psi	ISO 2039-1
Tensile Strength at Break	180 MPa	26100 psi	ISO 527
Elongation at Break	4.0 %	4.0 %	ISO 527
Tensile Modulus	9.50 GPa	1380 ksi	ISO 527
Flexural Strength	230 MPa	33400 psi	ISO 178
Flexural Modulus	7.70 GPa	1120 ksi	ISO 178
Charpy Impact Unnotched	4.00 J/cm ²	19.0 ft-lb/in ²	DIN 53453
	NB	NB	ISO 179/1eU
	3.60 J/cm ²	17.1 ft-lb/in ²	DIN 53453
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	DIN 53453
	0.900 J/cm ²	4.28 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	ISO 3146 DSC

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	130 °C	266 °F	Continuous; FRISETTA Test Method
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	550 V	550 V	CTI 100; IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China