

## Nilit FRIANYL A63 KV15 Nylon 6.6 for injection molding, 15% glass ball reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66

### Material Notes:

Nylon 6.6 for injection molding. Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nilit-FRIANYL-A63-KV15-Nylon-66-for-injection-molding-15-glass-ball-reinforced.php](http://www.lookpolymers.com/polymer_Nilit-FRIANYL-A63-KV15-Nylon-66-for-injection-molding-15-glass-ball-reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in <sup>3</sup>	ISO 1183
Water Absorption	1.7 - 2.7 %	1.7 - 2.7 %	ISO 62
Water Absorption at Saturation	6.0 - 8.0 %	6.0 - 8.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.012 - 0.020 cm/cm	0.012 - 0.020 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	161 MPa	23400 psi	ISO 2039-1
Tensile Strength at Break	83.0 MPa	12000 psi	ISO 527
Elongation at Break	7.0 %	7.0 %	ISO 527
Tensile Modulus	3.50 GPa	508 ksi	ISO 527
Flexural Strength	98.0 MPa	14200 psi	ISO 178
Flexural Modulus	3.20 GPa	464 ksi	ISO 178
Charpy Impact Unnotched	2.40 J/cm <sup>2</sup>	11.4 ft-lb/in <sup>2</sup>	DIN 53453
	3.50 J/cm <sup>2</sup>	16.7 ft-lb/in <sup>2</sup>	ISO 179/1eU
	2.00 J/cm <sup>2</sup> @Temperature -40.0 °C	9.52 ft-lb/in <sup>2</sup> @Temperature -40.0 °F	DIN 53453
Charpy Impact Unnotched	3.00 J/cm <sup>2</sup> @Temperature -30.0 °C	14.3 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 179/1eU
	0.500 J/cm <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	ISO 179/1eA
Charpy Impact, Notched	0.500 J/cm <sup>2</sup>	2.38 ft-lb/in <sup>2</sup>	DIN 53453

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	ISO 3146 DSC
Maximum Service Temperature, Air	100 °C	212 °F	Continuous; FRISETTA Test Method
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	550 V	550 V	CTI 100; IEC 112

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China