

## Nilit Nilamid B3 H ZB Unfilled, Low Temperature Impact Resistant PA6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Impact Grade

### Material Notes:

Description: Nilamid B3 H ZB is a high impact NYLON 6. The product has excellent impact properties, even at minus temperatures, whilst maintaining mechanical characteristics. Application areas include sports equipment, automotive components and industrial components subjected to shock loads. Key characteristics: Good impact strength, even at minus temperatures High elongation Good overall mechanical performance Excellent surface finish Information provided by NILIT.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nilit-Nilamid-B3-H-ZB-Unfilled-Low-Temperature-Impact-Resistant-PA6.php](http://www.lookpolymers.com/polymer_Nilit-Nilamid-B3-H-ZB-Unfilled-Low-Temperature-Impact-Resistant-PA6.php)

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in <sup>3</sup>	ASTM D792, ISO 1183
Water Absorption	2.0 %	2.0 %	23°C, 24h in H <sub>2</sub> O; sim. ISO 62
Water Absorption at Saturation	8.5 %	8.5 %	sim. ISO 62
Linear Mold Shrinkage, Flow	0.014 cm/cm	0.014 in/in	Euronil
Linear Mold Shrinkage, Transverse	0.014 cm/cm	0.014 in/in	Euronil

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.0 MPa	8700 psi	ISO 527, ASTM D638
Elongation at Yield	>= 100 %	>= 100 %	ISO 527, ASTM D638
Flexural Yield Strength	90.0 MPa	13100 psi	ISO 178, ASTM D790
Flexural Modulus	2.10 GPa	305 ksi	ISO 178, ASTM D790
Izod Impact, Notched (ISO)	9.00 kJ/m <sup>2</sup>	4.28 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	20.0 kJ/m <sup>2</sup>	9.52 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	NB	NB	ISO 179
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	2.10 J/cm <sup>2</sup>	9.99 ft-lb/in <sup>2</sup>	ISO 179
	0.650 J/cm <sup>2</sup>	3.09 ft-lb/in <sup>2</sup>	
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Mechanical Properties	Metric	English	Comments
<b>Thermal Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Maximum Service Temperature, Air	85.0 °C	185 °F	20,000 hr; IEC 216
Deflection Temperature at 0.46 MPa (66 psi)	167 °C	333 °F	ISO 75, ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	ISO 75, ASTM D648
Vicat Softening Point	180 °C	356 °F	49 N; ISO 306, ASTM D1525
	210 °C	410 °F	9.8 N; ISO 306, ASTM D1525
Flammability, UL94	HB	HB	
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Glow Wire Test	650 °C	1200 °F	Glow Wire Flammability Index; IEC 694-2-12
	@Thickness 3.20 mm	@Thickness 0.126 in	
	650 °C	1200 °F	Glow Wire Flammability Index; IEC 694-2-12
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Dielectric Strength	18.0 kV/mm	457 kV/in	ASTM D149
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Comparative Tracking Index	550 V	550 V	Sol. B; IEC 112, UL 746A
	@Thickness 3.20 mm	@Thickness 0.126 in	
	600 V	600 V	Sol. A; IEC 112, UL 746A
	@Thickness 3.20 mm	@Thickness 0.126 in	

Processing Properties	Metric	English	Comments
Nozzle Temperature	240 - 270 °C	464 - 518 °F	
Zone 1	230 - 260 °C	446 - 500 °F	hopper
Zone 2	230 - 260 °C	446 - 500 °F	
Zone 3	240 - 270 °C	464 - 518 °F	
Zone 4	240 - 270 °C	464 - 518 °F	

Melt Temperature Processing Properties	240 - 280 °C Metric	464 - 536 °F English	Do not melt above 300°C Comments
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	80°C is Preferred
Drying Temperature	80.0 - 85.0 °C	176 - 185 °F	
Dry Time	4 hour	4 hour	
Injection Pressure	70.0 - 100 MPa	10200 - 14500 psi	

Descriptive Properties	Value	Comments
Clamping Force	in tons, 0.7 times the projected surface area in cm <sup>2</sup>	
Heat Resistance - Ball Test	OK	at 125°C, IEC 309
	OK	at 165°C, IEC 309
Holding Pressure	90 MPa	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China