

Nye Lubricants 374CT (RL) Synthetic Oil

Category : Fluid , Lubricant , Lithium Gellant , Organic Soap Gellant , Polyalphaolefin (PAO)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-374CT-RL-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	131	131	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	61 cSt	61 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	9.5 cSt	9.5 cSt	Base Oil; ASTM D445

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	183	183	ASTM D217
Penetration P(60), 1/10 mm	179	179	ASTM D217
Oil Separation	0.00 %	0.00 %	24 hrs, 150C; FTM 719B, 321.2

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	Recommended
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	Recommended
Pour Point	-56.0 °C	-68.8 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PAO	
Gellant Type	Li soap	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China