

Nye Lubricants 733 (RL) Synthetic Oil

Category : Fluid , Lubricant , Clay Gellant , Polyalphaolefin (PAO)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-733-RL-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	127	127	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	32 cSt	32 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	5.4 cSt	5.4 cSt	Base Oil; ASTM D445
Evaporation Loss	12 %	12 %	22 hrs, 175C; ASTM D972

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	300	300	ASTM D217
Penetration P(60), 1/10 mm	315	315	ASTM D217
Oil Separation	10 %	10 %	22 hrs, 175C; FTM 719B, 321.2

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	Recommended
Minimum Service Temperature, Air	-54.0 °C	-65.2 °F	Recommended
Pour Point	-62.0 °C	-79.6 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PAO	
Gellant Type	Clay	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China