

## **OMG Americas GlidCop® AL-15 Dispersion Strengthened Copper**

Category: Metal, Metal Matrix Composite, Nonferrous Metal, Copper Alloy

## **Material Notes:**

GlidCop® AL-15 is copper that is dispersion strengthened with 0.3 wt% ultrafine particles of aluminum oxide. It is produced using an internal oxidation powder metallurgy process whereby aluminum oxide is formed in the Cu matrix. The matrix is hardened while the Cu electrical and thermal conductivity are minimally lowered. The aluminum oxide particles are very thermally stable and remain effective in strengthening the copper matrix and resisting grain coarsening even after very long exposures to high temperatures as in brazing or high temp duty cycles. GlidCop® is available with three different levels of Al2O3. Increasing the Al2O3 levels will increase strength but decrease conductivities. All three grades can be further strengthened by cold work. GlidCop® is available in a wide range of extruded and drawn shapes and sizes, including rounds, rectangles, wire, plates, tubes, and strip. Available on a limited basis in powder form. Information provided by OMG Americas.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_OMG-Americas-GlidCop-AL-15-Dispersion-Strengthened-Copper.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	255 - 300 MPa	37000 - 43500 psi	With 0% cold work

Thermal Properties	Metric	English	Comments
Thermal Conductivity	365 W/m-K	2530 BTU-in/hr-ft <sup>2</sup> -°F	

Component Elements Properties	Metric	English	Comments	
Al203	0.30 %	0.30 %		
Copper, Cu	99.7 %	99.7 %		

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000185 ohm-cm	0.00000185 ohm-cm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China