## **Oceanchem Group Tris (2-chloroisopropyl) Phosphate (TCPP)**

Category : Other Engineering Material , Additive/Filler for Polymer

## Material Notes:

Molecular Formula: C9H18O4Cl13PCas No.: 13674-84-5Property: It is colorless transparent oily liquid. Soluble in ethanol and chloroform, insoluble in aliphatic hydrocarbon, water solubility is less than 1%.Use: It is mainly used as soft or hard polyurethane foam, epoxy resin polystyrene, acrylic acid, cellulose acetate, ethyl cellulose paint, phenolic plastics, polyvinyl acetate and foam leak sealing agent. It has good heat conductivity and hydrolysis stabilizer, especially suitable for ASTME84 (grade). Its products have low viscosity in low temperature when it is used in polyurethane foam, unsaturated polyester and phenolic plastic.Storage and Packing: 250kg in galvanizing pail, storage temperature 5-38°C, in dry air, common chemicals.Information Provided by Oceanchem Group

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Oceanchem-Group-Tris-2-chloroisopropyl-Phosphate-TCPP.php

Physical Properties	Metric	English	Comments
Specific Grovity	1.29 g/cc	1.29 g/cc	
Specific Gravity	@Temperature 20.0 °C	@Temperature 68.0 °F	
Molecular Weight	327.4 g/mol	327.4 g/mol	

Thermal Properties	Metric	English	Comments	
Flash Point	220 °C	428 °F	open	

Optical Properties	Metric	English	Comments
Refractive Index	1.46 - 1.466	1.46 - 1.466	n20D1

Component Elements Properties	Metric	English	Comments	
Chlorine, Cl	32.5 %	32.5 %		
Phosphorous, P	9.46 %	9.46 %		

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.080 %	<= 0.080 %	

Descriptive Properties	Value	Comments
Acidity	<0.05	mg KOH/g
Appearance	Colorless or light yellow oily transparent liquid	
CAS Number	13674-84-5	
Chroma	50	Pt-Co

Descriptive Properties

Value

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China