

## Okulen® 1000 PE-UHMW, Multi-color

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), UHMW PE Ultra High Molecular Weight

### Material Notes:

OKULEN® 1000 is an ultra high molecular low pressure polyethylene with a molecular weight of < 3.5 g/mol. It has great wear resistance, high impact strength, and excellent sliding properties ideal for applications like machine construction, plant construction, and conveyor technology.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Okulen-1000-PE-UHMW-Multi-color.php](http://www.lookpolymers.com/polymer_Okulen-1000-PE-UHMW-Multi-color.php)

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in <sup>3</sup>	ISO 1183-A

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	64	64	ISO 868
Tensile Strength, Yield	14.0 - 17.0 MPa	2030 - 2470 psi	50 mm/min; ISO/R 527
Elongation at Break	>= 50 %	>= 50 %	50 mm/min; ISO/R 527
Creep Strength	10.0 MPa	1450 psi	
Coefficient of Friction, Dynamic	0.15 @Pressure 2.00 MPa	0.15 @Pressure 290 psi	PE-metal, V = 10 m/min; ASTM D1894
Coefficient of Friction, Static	0.20 @Pressure 2.00 MPa	0.20 @Pressure 290 psi	PE-metal, V = 10 m/min; ASTM D1894
Abrasion	145	145	Slurry-Test rel to GUR 4120 = 100%; DIN 58836

Thermal Properties	Metric	English	Comments
CTE, linear	200 µm/m-°C	111 µin/in-°F	DIN 53752
Melting Point	135 - 137 °C	275 - 279 °F	DSC ISO 3146
Maximum Service Temperature, Air	80.0 °C	176 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	<= 1.00e+14 ohm-cm	<= 1.00e+14 ohm-cm	Teil 30; IEC 600093 / VDE 0303

Descriptive Properties	Value	Comments
FDA Approved	No	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**