

Ovation Polymers SOFTAPLAS™ S 93A Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Thermoplastic Elastomer – Low tensile set, hydrolytic Stability and excellent balance of properties. *All properties are measured after 48 hours of conditioning at 23°C and 50% relative humidity. All samples are prepared according to ASTM standards. Variations within normal tolerances are possible for various types of colors and functional properties like UV resistance. Information provided by Ovation Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ovation-Polymers-SOFTAPLAS-S-93A-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.03 g/cc	1.03 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	91 - 93	91 - 93	15 sec; ASTM D2240
Elongation at Break	>= 400 %	>= 400 %	50 mm/min; ASTM D638
Izod Impact, Notched	NB	NB	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China