

Overview of materials for Polypropylene with 30% Calcium Carbonate (CaCO₃) Filler

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Calcium Carbonate (CaCO₃) Filler

Material Notes:

This property data is a summary of similar materials in the MatWeb database for the category "Polypropylene with 30% Calcium Carbonate (CaCO₃) Filler". Each property range of values reported is minimum and maximum values of appropriate MatWeb entries. The comments report the average value, and number of data points used to calculate the average. The values are not necessarily typical of any specific grade, especially less common values and those that can be most affected by additives or processing methods.

Order this product through the following link:

[http://www.lookpolymers.com/polymer_Overview-of-materials-for-Polypropylene-with-30-Calcium-Carbonate-CaCO₃-Filler.php](http://www.lookpolymers.com/polymer_Overview-of-materials-for-Polypropylene-with-30-Calcium-Carbonate-CaCO3-Filler.php)

Physical Properties	Metric	English	Comments
Density	1.01 - 1.17 g/cc	0.0365 - 0.0423 lb/in ³	Average value: 1.13 g/cc Grade Count:64
Filler Content	25.0 - 33.0 %	25.0 - 33.0 %	Average value: 29.9 % Grade Count:27
Water Absorption	0.0200 - 0.0400 %	0.0200 - 0.0400 %	Average value: 0.0250 % Grade Count:8
Linear Mold Shrinkage	0.00150 - 0.0200 cm/cm	0.00150 - 0.0200 in/in	Average value: 0.0119 cm/cm Grade Count:53
Melt Flow	1.00 - 280 g/10 min	1.00 - 280 g/10 min	Average value: 19.3 g/10 min Grade Count:41
Ash	29.1 - 30.0 %	29.1 - 30.0 %	Average value: 29.9 % Grade Count:12

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	48.0 - 107	48.0 - 107	Average value: 81.2 Grade Count:20
Hardness, Shore D	65.0 - 73.0	65.0 - 73.0	Average value: 70.2 Grade Count:9
Tensile Strength, Ultimate	11.0 - 28.0 MPa	1600 - 4060 psi	Average value: 20.4 MPa Grade Count:30
Tensile Strength, Yield	13.0 - 70.0 MPa	1890 - 10200 psi	Average value: 24.7 MPa Grade Count:45
Elongation at Break	3.10 - 500 %	3.10 - 500 %	Average value: 68.7 % Grade Count:47
Elongation at Yield	3.00 - 50.0 %	3.00 - 50.0 %	Average value: 7.40 % Grade Count:21
Modulus of Elasticity	1.20 - 3.03 GPa	174 - 440 ksi	Average value: 1.96 GPa Grade Count:18
Flexural Yield Strength	17.0 - 110 MPa	2470 - 16000 psi	Average value: 36.9 MPa Grade Count:38
Flexural Modulus	1.00 - 5.24 GPa	145 - 760 ksi	Average value: 1.94 GPa Grade Count:63

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched	0.200 - 6.41 J/cm	0.375 - 12.0 ft-lb/in	Average value: 0.959 J/cm Grade Count:58
Izod Impact, Unnotched	3.74 - 16.0 J/cm	7.00 - 30.0 ft-lb/in	Average value: 9.28 J/cm Grade Count:13
Izod Impact, Notched (ISO)	3.40 - 14.0 kJ/m²	1.62 - 6.66 ft-lb/in²	Average value: 6.40 kJ/m² Grade Count:4
Gardner Impact	1.24 - 40.7 J	0.917 - 30.0 ft-lb	Average value: 14.2 J Grade Count:18
	20.7892 - 20.7892 J @Temperature -30.0 - - 30.0 °C	15.3334 - 15.3334 ft-lb @Temperature -22.0 - - 22.0 °F	Average value: 20.8 J Grade Count:1

Thermal Properties	Metric	English	Comments
Melting Point	160 - 182 °C	320 - 360 °F	Average value: 168 °C Grade Count:4
Deflection Temperature at 0.46 MPa (66 psi)	43.0 - 159 °C	109 - 318 °F	Average value: 101 °C Grade Count:48
Deflection Temperature at 1.8 MPa (264 psi)	42.2 - 111 °C	108 - 232 °F	Average value: 63.3 °C Grade Count:40
Vicat Softening Point	94.0 - 152 °C	201 - 306 °F	Average value: 122 °C Grade Count:7
Flammability, UL94	HB	HB	Grade Count:21

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	Average value: 1.00e+16 ohm-cm Grade Count:4

Processing Properties	Metric	English	Comments
Processing Temperature	193 - 227 °C	380 - 440 °F	Average value: 210 °C Grade Count:4
Nozzle Temperature	200 - 232 °C	392 - 450 °F	Average value: 216 °C Grade Count:5
Melt Temperature	170 - 302 °C	338 - 576 °F	Average value: 217 °C Grade Count:12
Mold Temperature	4.00 - 91.0 °C	39.2 - 196 °F	Average value: 45.4 °C Grade Count:14
Drying Temperature	65.6 - 82.2 °C	150 - 180 °F	Average value: 76.3 °C Grade Count:8
Moisture Content	0.0100 - 0.0500 %	0.0100 - 0.0500 %	Average value: 0.0340 % Grade Count:5
Injection Pressure	2.76 - 103 MPa	400 - 15000 psi	Average value: 59.6 MPa Grade Count:9

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China