

## Oxford Polymers Oxnilon 66-43GF 43% Glass Fiber Filled Nylon 66 for Injection Molding

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled

**Material Notes:**

43% Glass Fiber Filled Nylon 66 for Injection Molding Information provided by Oxford Polymers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Oxford-Polymers-Oxnilon-66-43GF-43-Glass-Fiber-Filled-Nylon-66-for-Injection-Molding.php](http://www.lookpolymers.com/polymer_Oxford-Polymers-Oxnilon-66-43GF-43-Glass-Fiber-Filled-Nylon-66-for-Injection-Molding.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792
Filler Content	43 %	43 %	
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	193 MPa	28000 psi	ASTM D638
Tensile Strength, Yield	190 MPa	27500 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	262 MPa	38000 psi	ASTM D790
Flexural Modulus	10.3 GPa	1500 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Temperature 23.0 °C	2.00 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	262 °C	504 °F	
Deflection Temperature at 1.8 MPa (264 psi)	252 °C	485 °F	ASTM D648

Processing Properties	Metric	English	Comments
Processing Temperature	288 - 304 °C	550 - 580 °F	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China