

## PEAK Werkstoff DISPAL S260 Aluminum Alloy, AlSi25Cu4Mg, Condition T7

Category : Metal , Nonferrous Metal , Aluminum Alloy

### Material Notes:

Heat Treatment Condition T7 (Quenching in water at RT)Excellent properties:abrasive stabilityhigh stiffness (E-modulus)resistance even at high temperaturesgood grindabilityPEAK DISPAL materials allow the manufacturing of pistons for highest operational demands.Information provided by PEAK Werkstoff GmbH

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_PEAK-Werkstoff-DISPAL-S260-Aluminum-Alloy-AlSi25Cu4Mg-Condition-T7.php](http://www.lookpolymers.com/polymer_PEAK-Werkstoff-DISPAL-S260-Aluminum-Alloy-AlSi25Cu4Mg-Condition-T7.php)

Physical Properties	Metric	English	Comments
Density	2.527 - 2.793 g/cc	0.09129 - 0.1009 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	>= 168	>= 168	HV30
Tensile Strength at Break	>= 364 MPa	>= 52800 psi	
	@Temperature 150 °C	@Temperature 302 °F	
Tensile Strength, Yield	>= 421 MPa	>= 61100 psi	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Elongation at Break	>= 0.55 %	>= 0.55 %	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Modulus of Elasticity	>= 0.80 %	>= 0.80 %	
	@Temperature 150 °C	@Temperature 302 °F	
Poissons Ratio	>= 80.0 GPa	>= 11600 ksi	
	@Temperature 150 °C	@Temperature 302 °F	
Poissons Ratio	>= 92.0 GPa	>= 13300 ksi	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Poissons Ratio	0.277	0.277	Condition F
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	101.5 MPa	14720 psi	P50% rotary bending values for

Fatigue Strength Mechanical Properties	Metric @ Temperature 150 °C	English @ Temperature 302 °F	5X10 <sup>7</sup> cycles Comments
	206.5 MPa	29950 psi	P50% rotary bending values for 5X10 <sup>7</sup> cycles
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	16.7 - 17.7 µm/m-°C	9.28 - 9.83 µin/in-°F	
	@Temperature 20.0 - 100 °C	@Temperature 68.0 - 212 °F	
	17.5 - 18.5 µm/m-°C	9.72 - 10.3 µin/in-°F	
	@Temperature 20.0 - 200 °C	@Temperature 68.0 - 392 °F	
	18.3 - 19.3 µm/m-°C	10.2 - 10.7 µin/in-°F	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Specific Heat Capacity	0.860 - 0.900 J/g-°C	0.206 - 0.215 BTU/lb-°F	
Thermal Conductivity	124.1 W/m-K	861.3 BTU-in/hr-ft <sup>2</sup> -°F	
	@Temperature 400 °C	@Temperature 752 °F	
	131.5 W/m-K	912.6 BTU-in/hr-ft <sup>2</sup> -°F	
	@Temperature 200 °C	@Temperature 392 °F	
	131.9 W/m-K	915.4 BTU-in/hr-ft <sup>2</sup> -°F	
	@Temperature 300 °C	@Temperature 572 °F	
	132.7 W/m-K	920.9 BTU-in/hr-ft <sup>2</sup> -°F	
	@Temperature 100 °C	@Temperature 212 °F	
	135.5 W/m-K	940.4 BTU-in/hr-ft <sup>2</sup> -°F	
	@Temperature 30.0 °C	@Temperature 86.0 °F	
Melting Point	504 - 778 °C	939 - 1430 °F	
Solidus	504.1 - 510.1 °C	939.4 - 950.2 °F	
Liquidus	772.1 - 778.1 °C	1422 - 1433 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	70 %	70 %	As Balance
Copper, Cu	4.0 %	4.0 %	

Component Elements Properties	Metric	English	Comments
Silicon, Si	25 %	25 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000670 - 0.00000720 ohm-cm	0.00000670 - 0.00000720 ohm-cm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China