

PTS POM-270 Acetal Copolymer

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Information provided by PTS LLC.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PTS-POM-270-Acetal-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.41 g/cc	1.41 g/cc	ISO 1183
Linear Mold Shrinkage, Flow	0.018 - 0.022 cm/cm	0.018 - 0.022 in/in	Horizontal
Melt Flow	27 g/10 min @Load 2.16 kg, Temperature 190 °C	27 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	80	80	ISO 2039-2
Tensile Strength at Break	63.0 MPa	9140 psi	ISO 527-1/2
Elongation at Break	30 %	30 %	ISO 527-1/2
Tensile Modulus	2.55 GPa	370 ksi	ISO 527-1/2
Flexural Strength	90.0 MPa	13100 psi	ISO 178
Flexural Modulus	2.35 GPa	341 ksi	ISO 178
Izod Impact, Notched (ISO)	5.30 kJ/m ²	2.52 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear	120 µm/m-°C	66.7 µin/in-°F	ISO 11359
Melting Point	165 °C	329 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	ISO 75

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China