

PTS Trimid® N66-G43HL 43% Glass Fiber Reinforced Heat Stabilized, Lubed Nylon 6/6

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 40% Glass Fiber Filled

Material Notes:

Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

http://www.lookpolymers.com/polymer_PTS-Trimid-N66-G43HL-43-Glass-Fiber-Reinforced-Heat-Stabilized-Lubed-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	193.1 MPa	28010 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Modulus	10.34 GPa	1500 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	254 °C	489 °F	ASTM D789
Deflection Temperature at 1.8 MPa (264 psi)	251 °C	484 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	254 °C	490 °F	
Middle Barrel Temperature	268 °C	515 °F	
Front Barrel Temperature	285 °C	545 °F	
Nozzle Temperature	266 - 282 °C	510 - 540 °F	
Melt Temperature	271 - 293 °C	520 - 560 °F	
Mold Temperature	26.7 - 93.3 °C	80.0 - 200 °F	
Drying Temperature	71.1 °C	160 °F	
Dry Time	4 hour	4 hour	
Injection Pressure	68.9 MPa	10000 psi	

Processing Properties	Metric	English	Comments
Screw Speed	30 - 60 rpm	30 - 60 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China