

Palm Labs Adhesives TURBO FUSE SERIES 180 BLACK TOUGHENED (2400 Viscosity) Rapid Bonding Adhesive

Category : Polymer , Adhesive

Material Notes:

Palm Lab's Cyanoacrylate is a one component rapid bonding adhesive. TURBO FUSE SERIES 440 - GEL BLACK TOUGHENED advanced thixotropic formula is designed to polymerize instantly by absorbing surface moisture. The product's performance has been tested with a variety of materials, and is recommended for a multitude of applications. The fast curing qualities make it especially desirable in high speed industrial production. TURBO FUSE SERIES 440 - GEL BLACK TOUGHENED is ideal for use in applications that require a gel like, viscous adhesive. It is also ideal for applications on vertical, angled or overhead surfaces. For extreme gap fill, the use of an accelerator is highly recommended. Because of the thick gel consistency, it works especially well in poor fitting applications such as rough metal or ceramic repair, unfinished metal to metal bonding, and metal to rubber. The BLACK TOUGHENED formula is especially good for sound speakers. Part Numbers for this data: 06-440B, 07-440B, 08-440B, 09-440B, S09-440B, 35-440B Soluble in Acetone, MEK, Amide, Methylene Chloride Information provided by Palm Laboratories Adhesives

Order this product through the following link:

http://www.lookpolymers.com/polymer_Palm-Labs-Adhesives-TURBO-FUSE-SERIES-180-BLACK-TOUGHENED-2400-Viscosity-Rapid-Bonding-Adhesive.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	Liquid State

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	65	65	Cured State
Shear Strength	17.2 MPa	2500 psi	Tensile, (Cured State)

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	82.2 °C	180 °F	Cured State
Softening Point	149 °C	300 °F	Cured State
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	Cured State
Flash Point	76.7 - 93.3 °C	170 - 200 °F	Liquid State

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.33	3.33	Cured State
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Shelf Life Processing Properties	6.00 Month Metric	6.00 Month English	Liquid State Comments
Descriptive Properties	Value		Comments
Appearance	Black Gel		Liquid State
	Black-Hard		Cured State
Base compound (Resin)	Ethyl Cyanoacrylate		Liquid State
Gap Fill	0.010"		Cured State
Material Set Up Time	<90 sec		Phenolic to Phenolic
	15-30 sec		Rubber to Rubber
	20-40 sec		Aluminum to Aluminum
	50-100 sec		Steel to Steel
	50-80 sec		Polycarbonate to Polycarbonate

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China