

## Palm Labs Adhesives Turbo Fuse Series 180 (2400 Viscosity) Rapid Bonding Adhesive

Category: Polymer, Adhesive, Thermoset, Acrylic/Cyanoacrylate Adhesive

## **Material Notes:**

Palm Lab's Cyanoacrylate is a one component rapid bonding adhesive. TURBO FUSE SERIES 180 advanced formula is designed to polymerize instantly by absorbing surface moisture. The product's performance has been tested with a variety of materials, and is recommended for a multitude of applications. The fast curing qualities make it especially desirable in high speed industrial production. TURBO FUSE SERIES 180 is ideal for use in applications that require an easily handled high viscosity adhesive. Because of the 2400 viscosity, it works especially well in bonding porous surfaces like ceramics, and is excellent for bonding metal and rubber parts.Part Numbers for this data: 04-180, 10-180, 15-180, 20-180, 25-180, 30-180, 35-180Soluble in Acetone, MEK, Amide, Methylene ChlorideInformation provided by Palm Laboratories Adhesives

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Palm-Labs-Adhesives-Turbo-Fuse-Series-180-2400-Viscosity-Rapid-Bonding-Adhesive.php

| Physical Properties | Metric         | English        | Comments     |
|---------------------|----------------|----------------|--------------|
| Specific Gravity    | 1.05 g/cc      | 1.05 g/cc      | Liquid State |
| Viscosity           | 2300 - 2500 cP | 2300 - 2500 cP | Liquid State |

| Mechanical Properties | Metric   | English  | Comments               |
|-----------------------|----------|----------|------------------------|
| Hardness, Barcol      | 65       | 65       | Cured State            |
| Shear Strength        | 17.2 MPa | 2500 psi | Tensile, (Cured State) |

| Thermal Properties               | Metric         | English      | Comments                            |
|----------------------------------|----------------|--------------|-------------------------------------|
| Maximum Service Temperature, Air | 82.2 °C        | 180 °F       | Cured State                         |
| Softening Point                  | 149 °C         | 300 °F       | Cured State                         |
| Minimum Service Temperature, Air | -53.9 °C       | -65.0 °F     | Cured State                         |
| Flash Point                      | 76.7 - 93.3 °C | 170 - 200 °F | Liquid State (Tagliabue closed cup) |

| Electrical Properties | Metric                   | English                  | Comments    |
|-----------------------|--------------------------|--------------------------|-------------|
|                       | 3.33                     | 3.33                     |             |
| Dielectric Constant   | @Frequency 1.00e+6<br>Hz | @Frequency 1.00e+6<br>Hz | Cured State |

| Processing Properties | Metric     | English    | Comments     |
|-----------------------|------------|------------|--------------|
| Shelf Life            | 12.0 Month | 12.0 Month | Liquid State |



| Descriptive Properties | Value               | Comments                       |
|------------------------|---------------------|--------------------------------|
| Appearance             | Clear liquid        | Liquid State                   |
|                        | Clear-Hard          | Cured State                    |
| Base compound (Resin)  | Ethyl Cyanoacrylate | Liquid State                   |
| Gap Fill               | 0.008"              | Cured State                    |
| Material Set Up Time   | <10 sec             | Rubber to Rubber               |
|                        | <20 sec             | Aluminum to Aluminum           |
|                        | <40 sec             | Phenolic to Phenolic           |
|                        | 30-50 sec           | Steel to Steel                 |
|                        | 50-70 sec           | Polycarbonate to Polycarbonate |

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype : lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China